

Grande		Composición química del acero inoxidable								
		C	Si	Mn	P	S	Ni	Cr	Mo	N
ASTM A240	304	≤0.080	≤0.75	≤2.00	≤0.045	≤0.030	8.0≈10.5	18.0≈20.0	--	≤0.10
	304L	≤0.030	≤0.75	≤2.00	≤0.045	≤0.030	8.0≈12.0	18.0≈20.0	--	≤0.10
	316	≤0.080	≤0.75	≤2.00	≤0.045	≤0.030	10.0≈14.0	16.0≈18.0	2.0≈3.0	≤0.10
	316L	≤0.030	≤0.75	≤2.00	≤0.045	≤0.030	10.0≈14.0	16.0≈18.0	2.0≈3.0	≤0.10
	430	≤0.120	≤1.00	≤1.00	≤0.040	≤0.030	≤0.75	16.0≈18.0	--	--