

TUBERÍA SCHEDULE

ASTM A312

Diámetro nominal	Diámetro exterior	Espesor nominal de pared					
		Schedule 10S			Schedule 40S		
		Espesor de pared (mm)	Peso (kg/m)		Espesor de pared (mm)	Peso (kg/m)	
			Grado			Grado	
			304	316		304	316
304L	316L		304L	316L			
1/4	13.72	1.65	0.50	0.50	2.24	0.64	0.64
3/8	17.15	1.65	0.64	0.64	2.31	0.85	0.86
1/2	21.34	2.11	1.1	01.02	2.77	1.28	1.26
3/4	26.67	2.11	1.29	1.30	2.87	1.70	1.71
1	33.40	2.77	2.11	2.13	3.38	2.53	2.54
1 1/4	42.16	2.77	2.72	2.74	3.56	3.42	3.45
1 1/2	48.26	2.77	3.14	3.16	3.68	4.09	4.11
2	60.33	2.77	3.97	4.00	3.91	5.50	5.53
2 1/2	73.03	3.05	5.32	5.35	5.16	8.72	8.78
3	88.90	3.05	6.52	6.56	5.49	11.4	11.5
3 1/2	101.60	3.05	7.49	7.54	5.74	13.7	13.8
4	114.30	3.05	8.45	8.51	6.0	16.2	16.3
5	141.30	3.4	11.7	11.8	6.55	22.0	22.1
6	168.28	3.4	14.0	14.1	7.11	28.5	28.
8	219.08	3.76	20.2	20.3	8.18	43.0	43.2
10	273.05	4.19	28.1	28.2	9.27	60.9	61.3